OUPONT >

MOLYKOTE[®] 7348 Silicone Grease

High-temperature silicone grease for rolling-element bearings

Features

- Low evaporation
- High oxidation resistance
- Good long-term lubrication
- High drop point
- Water-resistant

Composition

- Silicone oil
- Lithium complex thickener
- Antioxidant
- Solid lubricants

Applications

Used successfully on bearings in driers and on conveyor chains of wood coatings plants. Also suitable for sterilizers.

How to use

Clean bearing surfaces. Apply grease in the normal way using a brush, grease gun or automatic lubricating system. MOLYKOTE[®] 7348 Silicone Grease can be used in centralized lubrication systems.

Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Usable life and storage

When stored at or below 20°C in the original unopened containers, this product has a usable life of 60 months from the date of production.

Packaging

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest MOLYKOTE[®] sales office or MOLYKOTE[®] distributor.

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE[®] sales representative prior to writing specifications on this product.

ColorLight beigeConsistency, density, viscosity2DIN 51 818NLGI consistency class2ISO 2137Worked penetrationmm/10265-295ISO 2811Density at 20°Ca/ml1.09
Consistency, density, viscosity DIN 51 818 NLGI consistency class 2 ISO 2137 Worked penetration mm/10 265-295 ISO 2811 Density at 20°C a/ml 1.09
DIN 51 818NLGI consistency class2ISO 2137Worked penetrationmm/10265-295ISO 2811Density at 20°Cg/ml1.09
ISO 2137 Worked penetration mm/10 265-295
ISO 2811 Density at 20°C a/ml 1.09
DIN 51 562 Base oil viscosity at mm²/s 500 25°C
Temperature
Service temperature °C -20 to +230; +250 for sho periods
ISO 2176 Drop point °C >290
Load-carrying capacity
Four-ball tester
DIN 51 350 Weld load N 1,500 pt.4
Resistance
DIN 51 807 Water resistance, static 1-90 pt.1
DIN 51 808 Oxidation resistance, bar 0.1 pressure drop 100 h, 99°C
Oil separation
Oil separation
DIN 51 817 Standard test % 1.9

⁽¹⁾DIN: Deutsche Industrie Norm. ISO: International Standardization Organization.

 $DuPont^{\mathsf{TM}}$, the DuPont Oval Logo, and all trademarks and service marks denoted with $^{\mathsf{TM}}$, SM or $^{\otimes}$ are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

© 1997-2019 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.