

MOLYKOTE® Longterm W 2 High Performance Grease

White lubricating grease for metal/metal combinations with slow to fast movements and medium loads

Features

- · Good load-carrying capacity
- Suitable for long-term lubrication since it has no tendency to oxidize
- · Wear protection through solid lubricants
- · Good adhesion strength due to incorporated adhesion improver
- Good corrosion protection (corrosion step 0-1 in the SKF-Emcor test)
- Prevents the formation of frictional corrosion

Composition

- · Mineral oil
- · Lithium soap
- Solid lubricants
- Adhesion improver

Applications

Used successfully for bearings in machinery used in the food and pharmaceutical industries, textile and papermaking machines, domestic appliances, and mechanical precision instruments.

How to use

Clean the contact areas. Apply with brush, spatula, grease gun or automatic lubricating device. Can be used in central lubrication systems.

Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Usable life and storage

When stored at or below 20°C in the original unopened containers, this product has a usable life of 60 months from the date of production.

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

ош.оо .ор.ооо	manyo phon to writing of	o o modilo m	on and product	
Standard ⁽¹⁾	Test	Unit	Result	
	Color		White	
Consistency	, density, viscosity			
DIN 51 818	NLGI consistency class		2	
ISO 2137	Worked penetration	mm/10	265-295	
ISO 2811	Density at 20°C	g/ml	0.9	
DIN 51 562	Base oil viscosity at 40°C	mm²/s	125	
Temperature	•			
	Service temperature	°C	-30 to 110 +130 for short periods	
ISO 2176	Drop point	°C	>=180	
ASTM D1478-80	Low-temperature torque test at -20°C			
	Initial breakaway torque	Nm	125x10 ⁻³	
	Torque after 20 minutes running time	Nm	44x10 ⁻³	
Load-carrying capacity, wear protection, service life				
	Four-ball tester			
DIN 51 350 pt.4	Weld load	N	2,400	
DIN 51 350 pt.5	Wear scar under 800 N load	mm	1.4	
DIN 51821- 02-A	FAG roller element bearing tester FE 9, 1,500/6,000-110, F‡}	h	155	
(1) - 1 - 1				

⁽¹⁾DIN: Deutsche Industrie Norm. ISO: International Standardization Organization. ASTM: American Society for Testing and Materials.

Continued on next page

Typical properties (continued)

<i>,</i> ,		,		
Standard ⁽¹⁾	Test	Unit	Result	
Speed				
	DN value ⁽²⁾	mm/min	450,000	
Corrosion protection				
DIN 51 802	SKF-Emcor method Degree of corrosion		0-1	
Oil separation - evaporation				
	Oil bleeding, 24 h, 100°C	%	3.3	
	Oil evaporation, 24 h, 100°C	%	0.5	

⁽¹⁾DIN: Deutsche Industrie Norm. ISO: International Standardization Organization. ASTM: American Society for Testing and Materials. (2)DN values are calculated approximations and will vary widely with temperature, load and bearing type.

Packaging

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or [®] are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 1997-2019 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.